



# VEKA Recycling:

---

## Technical Factsheets

Grey white 9002.001

Processed from	PVC windows
Product description Product no.	Pellets, grey white 9002.001 80.0.9002.001
COLOUR VALUES (CIE Lab colour space)	L 89.0 (+ 1) a -0.70 b < 4.5
THERMAL STABILITY under DIN 53 381, test B, nitrogen as carrier gas	≈ 78 min
VICAT SOFTENING POINT under DIN ISO 306, test B/50	> 80 °C
YOUNG'S MODULUS under DIN EN ISO 527 – 1	≈ 2400 N/mm <sup>2</sup>
CHARPY IMPACT STRENGTH under DIN ISO 179/1eA	≈ 20.5 kJ/m <sup>2</sup>
K-VALUE viscosity measurement under DIN 53726	≈ 64
BULK DENSITY under DIN 53466	≈ 0.85 g/cm <sup>3</sup>
CONTAMINATION	< 0.02%

Subject to modifications and amendments

---