



VEKA Recycling:

Technical Factsheets

Traffic white 9016.001

Processed from	PVC windows
Product description Product no.	Pellets, traffic white 9016.001 80.0.9016.001
COLOUR VALUES (CIE Lab colour space)	L 90 (+ 1) a -1.70 b < 3
THERMAL STABILITY under DIN 53 381, test B, nitrogen as carrier gas	≈ 78 min
VICAT SOFTENING POINT under DIN ISO 306, test B/50	> 80 °C
YOUNG'S MODULUS under DIN EN ISO 527 – 1	≈ 2400 N/mm ²
CHARPY IMPACT STRENGTH under DIN ISO 179/1eA	≈ 20.5 kJ/m ²
K-VALUE viscosity measurement under DIN 53726	≈ 64
BULK DENSITY under DIN 53466	≈ 0.85 g/cm ³
CONTAMINATION	< 0.02%

Subject to modifications and amendments