



VEKA Recycling:

Technical Factsheets

Beige grey 7006.001

Processed from	PVC windows
Product description Product no.	Pellets, beige grey 7006.001 80.0.7006.001
COLOUR VALUES (CIE Lab colour space)	L 45-80 a k.A. b k.A.
THERMAL STABILITY under DIN 53 381, test B, nitrogen as carrier gas	≈ 78 min
VICAT SOFTENING POINT under DIN ISO 306, test B/50	> 76 °C
YOUNG'S MODULUS under DIN EN ISO 527 – 1	≈ 2400 N/mm ²
CHARPY IMPACT STRENGTH under DIN ISO 179/1eA	> 12 kJ/m ²
K-VALUE viscosity measurement under DIN 53726	≈ 64
BULK DENSITY under DIN 53466	≈ 0.85 g/cm ³
CONTAMINATION	< 0.1%

Subject to modifications and amendments
