



VEKA Recycling:

Technical Factsheets

Light grey 7035.001

| | |
|--|---|
| Processed from | PVC windows |
| Product description Product no. | Pellets, light grey 7035.001 80.0.7035.001 |
| COLOUR VALUES (CIE Lab colour space) | L 81.00 (+/-1) a -1.00 (+/-1) b 1.60 (+/-1) |
| THERMAL STABILITY under DIN 53 381, test B, nitrogen as carrier gas | ≈ 78 min |
| VICAT SOFTENING POINT under DIN ISO 306, test B/50 | > 80 °C |
| YOUNG'S MODULUS under DIN EN ISO 527 – 1 | ≈ 2400 N/mm ² |
| CHARPY IMPACT STRENGTH under DIN ISO 179/1eA | ≈ 20.5 kJ/m ² |
| K-VALUE viscosity measurement under DIN 53726 | ≈ 64 |
| BULK DENSITY under DIN 53466 | ≈ 0.85 g/cm ³ |
| CONTAMINATION | < 0.02% |

Subject to modifications and amendments
